



45 Higgins Avenue  
 Winnipeg, MB R3B 0A8  
 Tel: 204.339.6456  
 Fax: 204.334.1800  
 www.duxtonwindows.com

## Performance Values

### SERIES 328 - FiberWall™ Hi Profile

| Glass type   | Application     | LoE Surface | Gas   | Centre-of-Glass |         |           |               | Overall Window     |                  |           |               | Energy Star   |       |
|--|-----------------|-------------|-------|-----------------|---------|-----------|---------------|--------------------|------------------|-----------|---------------|---------------|-------|
|  |                 |             |       | R-Value         | U-Value | Heat Gain | Visible Light | U-Value (imperial) | U-Value (metric) | Heat Gain | Visible Light | Energy Rating | Zone  |
| <b>Dual Pane</b>   |                 |             |       |                 |         |           |               |                    |                  |           |               |               |       |
| Cardinal LoE-180   | High Solar Gain | 3           | Argon | 3.85            | 0.26    | 0.68      | 79%           | 0.26               | 1.48             | 0.53      | 61%           | 38            | 1 2 3 |
| Cardinal LoE-272   | Mid-Range       | 2           | Argon | 4.00            | 0.25    | 0.41      | 72%           | 0.25               | 1.42             | 0.32      | 55%           | 27            | 1 2   |
| Cardinal LoE-366   | Low Solar Gain  | 2           | Argon | 4.17            | 0.24    | 0.27      | 65%           | 0.24               | 1.36             | 0.21      | 50%           | 22            | 1 2   |
| <b>Triple Pane - 1 LoE Coating - High Performance</b>        |                 |             |       |                 |         |           |               |                    |                  |           |               |               |       |
| Cardinal LoE-180   | High Solar Gain | 5           | Argon | 5.56            | 0.18    | 0.61      | 73%           | 0.19               | 1.08             | 0.48      | 56%           | 44            | 1 2 3 |
| Cardinal LoE-272   | Mid-Range       | 2           | Argon | 5.26            | 0.19    | 0.38      | 66%           | 0.19               | 1.08             | 0.30      | 50%           | 33            | 1 2 3 |
| Cardinal LoE-366   | Low Solar Gain  | 2           | Argon | 5.56            | 0.18    | 0.25      | 59%           | 0.19               | 1.08             | 0.20      | 45%           | 28            | 1 2 3 |
| <b>Triple Pane - 2 LoE Coatings - Ultra High Performance</b> |                 |             |       |                 |         |           |               |                    |                  |           |               |               |       |
| Cardinal LoE-180 and 180                                     | High Solar Gain | 2 and 5     | Argon | 7.69            | 0.13    | 0.56      | 70%           | 0.15               | 0.85             | 0.43      | 54%           | 46            | 1 2 3 |
| Cardinal LoE-272 and 180                                     | Mid-Range       | 2 and 5     | Argon | 7.69            | 0.13    | 0.37      | 63%           | 0.15               | 0.85             | 0.29      | 49%           | 38            | 1 2 3 |
| Cardinal LoE-272 and 272                                     | Mid-Range       | 2 and 5     | Argon | 7.69            | 0.13    | 0.35      | 58%           | 0.14               | 0.79             | 0.27      | 44%           | 38            | 1 2 3 |
| Cardinal LoE-366 and 180                                     | Low Solar Gain  | 2 and 5     | Argon | 7.69            | 0.13    | 0.24      | 57%           | 0.14               | 0.79             | 0.19      | 44%           | 33            | 1 2 3 |
| Cardinal LoE-366 and 366                                     | Low Solar Gain  | 2 and 5     | Argon | 8.33            | 0.12    | 0.24      | 47%           | 0.14               | 0.79             | 0.18      | 36%           | 33            | 1 2 3 |

Performance Values are calculated by certified, 3rd party test labs. Information is gleaned from best available industry sources. The reader is cautioned that test results should be used for comparison purposes only. Results are size and installation dependent. In-service performance can be significantly different from those shown. Product tested indicates design potential. Model size was 1200 mm x 1500 mm.



45 Higgins Avenue  
Winnipeg, MB R3B 0A8  
Tel: 204.339.6456  
Fax: 204.334.1800  
[www.duxtonwindows.com](http://www.duxtonwindows.com)

## Performance Values

### *SERIES 328 - FiberWall™ Hi Profile*

#### Notes

- (1) 2-Pane calculations based on 2 tempered lites of 1/8" (3 mm) glass and 3/4" (20 mm) airspace.
- (2) 3-Pane calculations based on 3 tempered lites of 1/8" (3 mm) glass and two 1/2" (13 mm) airspaces. Available up to 6 mm glass.
- (3) Calculations for argon filled unit made with 90% Argon/ 10% air.
- (4) NFRC Environmental Conditions used for all values.
- (5) Cardinal Endur warm edge stainless steel spacer used for all values.
- (6) Thicker glass options available, up to 6 mm in dual pane or 5 mm in triple pane.